TECHNICAL DATA SHEET

Poly(butylene adipate-co-terephthalate)

Product Poly(butylene adipate-co-terephthalate) TECHNICAL DATA SHEET

Chemical Formula (C10H10O4.C6H10O4.C4H10O2)x

Cas No 55231-08-8 Interested in this chemical? Please contact us at

Description

PBAT is a thermoplastic biodegradable plastic. It not only has good ductility and elongation at break, but also has good heat resistance and impact properties.

Applications

Mainly applicable to blow molding processing of film ,products, typical products include but not limited to supermarket shopping bags, courier bags, clothing bags, industrial product package

Packaging

In 25kg kraft bag or 800/1200kg jumbo bag.

ITEMS	UNIT	METHOD	FC-2030	FM-0625	FS-0330	TH801T
Density	g/cm³	ISO1183	1.47±0.03	1.24±0.02	1.26-1.3	1.21
Hardness	D	ISO868	45±2	45±2	50-60	
Tensile Strengh	Мра	ISO527	16±2	16±2	2-4	≥25
Elongation At Break	%	ISO527	≥450	≥400	≥500	≥400
MVR 190℃,2KG	g/10 min	ISO1133	≤5	≤5	2-4	2.5-4.5
Melting Points	$^{\circ}$	ISO3146	95-135	95-135	95-150	116-122
Thermal Decomposition Temp	$^{\circ}$	ASTM D6370	360	230	260	

Copyright © Chemdo. All rights reserved. No part of this publication may be copied, downloaded, reproduced, stored in a retrieval system or transmitted in any form by any means, electronic, mechanical, photocopied, recorded or otherwise, without permission of the publisher. No representation or warranty is made as to the truth or accuracy of any data, information or opinions contained herein or as to their suitability for any purpose, condition or application. None of the data, information or opinions contained herein may be relied upon for any purpose or reason. Chemdo disclaims any liability, damages, losses or other consequences suffered or incurred in connection with the use of the data, information or opinions contained herein. In addition, nothing contained herein shall be construed as a recommendation to use any products in conflict with existing patents covering any material or its use.

