

TECHNICAL DATA SHEET

Polypropylene PPB-M09(K8009)

Product Polypropylene Resin PPB-M09(K8009)
HS code 39021000
Type PP Co-polymer
Print Date Oct 18th, 2020

TECHNICAL DATA SHEET

PPB-M09(K8009)

www.chemdo.com info@chemdo.com

Description

Polypropylene, a kind of non-toxic, odorless, tasteless opalescent polymer with high crystallization, the melting point among 164-170°C, the density among 0.90-0.91g/cm³, the molecular weight is about 80,000-150,000. PP is one of the lightest plastic of all varieties at present, particularly stable in water, with a water absorption rate in water for 24 hours is only 0.01%.

Application Direction

The grade produced by the HORIZONE gas-phase polypropylene process of Japanese JPP company. It is mainly used for making washing machine internal and external parts, automotive interior parts, automotive modified materials and other products.

Product Packaging

In 25kg bag, 16MT in one 20fcl without pallet or 26-28MT in one 40HQ without pallet or 700kg jumbo bag, 26-28MT in one 40HQ without pallet.

Typical Characteristic

ITEM	UNIT	INDEX	TEST METHOD
Melt mass flow(MFR) Standard value	g/10min	8.5	GB/T 3682.1-2018
Melt mass flow(MFR) Deviation value	g/10min	±1.0	GB/T 3682.1-2018
Tensile yield stress	Mpa	≥ 22.0	GB/T 1040.2-2006
Flexural modulus(Ef)	Mpa	≥ 1000	GB/T 9341-2008
Charpy notched impact strength (23°C)	KJ/m2	≥ 40	GB/T 1043.1-2008
Heat deflection temperature under load(Tf0.45)	°C	≥ 80	GB/T 1634.2-2019



Copyright © Chemdo. All rights reserved. No part of this publication may be copied, downloaded, reproduced, stored in a retrieval system or transmitted in any form by any means, electronic, mechanical, photocopied, recorded or otherwise, without permission of the publisher. No representation or warranty is made as to the truth or accuracy of any data, information or opinions contained herein or as to their suitability for any purpose, condition or application. None of the data, information or opinions contained herein may be relied upon for any purpose or reason. Chemdo disclaims any liability, damages, losses or other consequences suffered or incurred in connection with the use of the data, information or opinions contained herein. In addition, nothing contained herein shall be construed as a recommendation to use any products in conflict with existing patents covering any material or its use.