

POLYPROPYLENE T36F TYPICAL PROPERTIES

_	_		
$\mathbf{C}\mathbf{D}$		\mathbf{r}	
I-K	Δ		н
	$\overline{}$		

BOPP film grade

APPLICATIONS

- 1 Food packaging
- 2 Textile packaging
- 3 Metallized barrier film

CHARACTERISTICS

With outstanding optical properties, low ash level and maximum cleanliness

PROPERTIES

ITEM		UNIT		VALUE	METHOD	
1	Appearance	Transparency	/		/	SH/T 1541
2	Fish Eye	0.8mm	piece/1520cm ²	<	5	GB/T 6595
		0.4mm	piece/1520cm ²	\	30	
3 MFR		g/10min		3.0±0.5	GB/T 3682	
4 Isotactic Index		%		96.0±2	GB/T 2412	
5 Ash Content		mg/kg	<	300	GB/T 9345.1	
6 Tensile Strength at Yield		Мра	\wedge	30.0	GB/T 1040.2	
7	Haze		%	<	6.0	GB/T 2410

The figures listed in this guide are for reference purposes only; they are not to be used as specification limits.

Please note that this information provided herein might be updated without a previous notice.

Zhongjing Petrochemical makes no warranty of any kind, expressed or implied, regarding to the accuracy of these data For further requirements, please contact us.