


## Technical Data Sheet

### Moplen RP348RX B



Polypropylene, Random Copolymer

#### Product Description

Moplen RP348RX is a polypropylene random copolymer with good flowability which is used in injection molding applications.

Moplen RP348RX is nucleated, for improved productivity and very good optical properties (transparency and brilliance). Its antistatic additivition prevents dust deposits and eases items demolding.

Typical applications of Moplen RP348RX are caps & closures, housewares and rigid packaging items.

#### Regulatory Status

For regulatory compliance information, see Moplen RP348RX [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	China
<b>Application</b>	Caps & Closures; Housewares
<b>Market</b>	Consumer Products; Rigid Packaging
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Contains Antistat; High Transparency; Medium Flow; Nucleated; Random Copolymer

Typical Properties	Nominal	
	Value	Units
<b>Physical</b>		
Melt Flow Rate, (230 °C/2.16 kg)	25 g/10 min	ISO 1133-1
<b>Mechanical</b>		
Tensile Modulus	1150 MPa	ISO 527
Tensile Stress at Yield, (23 °C)	30 MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	14 %	ISO 527-1, -2
<b>Impact</b>		
Charpy Impact strength - notched at 23°C	6 kJ/m <sup>2</sup>	ISO 179
<b>Thermal</b>		
Vicat Softening Temperature, (A50)	130 °C	ISO 306
Deflection Temperature Under Load, (0.46 MPa, Unannealed)	76 °C	ISO 75B-1, -2

## **Notes**

These are typical property values not to be construed as specification limits.

## **Company Information**

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## **Disclaimer**

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## **Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.